

Diluted Type Series

TRADE NAME	EPOXY EQUIVALENCY (g/eq)	VISCOSITY (mPa.s/25°C)	COLOR (Gardner)	CHARACTERSTICS
GEKR114	190-210	500-1200	1MAX	C ₁₂ -C ₁₄ alkyl glycidyl ether diluted type
GEKR114L	184-194	800-1200*	1MAX	C ₁₂ -C ₁₄ alkyl glycidyl ether diluted type
GEKR115	175-195	400-1000	1MAX	Butyl glycidyl ether diluted type
GEKR253	206-215	6000-7000	1MAX	C ₁₂ -C ₁₄ alkyl glycidyl ether diluted type, suitable for adhesive,coating etc
GEKR257	182-192	400-600	3MAX	Cresyl glycidyl ether diluted type