

## UV Block Series

TRADE NAME	EPOXY EQUIVALENCY (g/eq)	VISCOSITY (mPa.s/25°C)	NON VOLATILITY (wt%)	BROMINE CONTENT (wt%)	CHARACTERSTICS
GEBR454A80	420-450	800-2000	79-81	18-21	FR4 yellow resin, good UV resistance effect
GEBR454HA80	360~410	800-2000	79-81	18-21	FR6 yellow resin, good UV resistance effect, Tg140°C
GEBR481A80	455-475	1000-2500	79-81	18-21	Good UV resistance effect, suitable for thin laminates