

High CTI Series

TRADE NAME	EPOXY EQUIVALENCY (g/eq)	VISCOSITY (mPa.s/25°C)	NON VOLATILITY (wt%)	BROMINE CONTENT (wt%)	CHARACTERSTICS
GEBR460A80	350-380	1000-2000	79-81	10~15	High CTI resin, CTI above 600V, flammability UL94,V-0
GEBR466A80	350-380	1000-2000	79-81	10~15	High CTI resin, CTI 600V, flammability UL94,V-0, good UV resistance effect