

CCL epoxy resin curing agent

TRADE NAME	VISCOSITY (mPa.s/25°C)	NON-VOLATILITY (wt%)	HYDROXY EQUIVALENCY(g/eq)	CHARACTERSTICS
GERH321K65	3000~7000	64.0~66.0	108	PN type, suitable for lead free process
GERH326K65	3500~7000	64.0~66.0	120	PN type, suitable for lead free process
GERH832K65	1800~3800	64.0~66.0	120	PN type, suitable for lead free process
GERH983K65	1500~3000	64.0~66.0	120	PN type, suitable for lead free process