

## Taffy Method Type 300 Series

| TRADE NAME | EPOXY<br>EQUIVALENCY<br>(g/eq) | HYDROLYZABLE<br>CHLORINE(ppm) | SOFTENING<br>POINT(°C) | COLOR (Gardner) | CHARACTERSTICS                                     |
|------------|--------------------------------|-------------------------------|------------------------|-----------------|----------------------------------------------------|
| GESR301    | 450-500                        | 500MAX                        | 65-75                  | 1MAX            | Low viscosity,low softening point and<br>high flow |
| GESR301H   | 520~580                        | 500MAX                        | 70~80                  | 1MAX            |                                                    |
| GESR302    | 600-700                        | 500MAX                        | 75-85                  | 1MAX            |                                                    |
| GESR303    | 800-900                        | 500MAX                        | 85-98                  | 1MAX            |                                                    |
| GESR304    | 890-970                        | —                             | 96-106                 | 1MAX            | high flow for coating                              |
| GESR307    | 1700-2100                      | —                             | 120-130                | 1MAX            |                                                    |