

## Master Batch Series

TRADENAME	EPOXY EQUIVALENCY (g/eq)	ICI VISCOSITY (P/150°C)	SOFTENING POINT(°C)	CHARACTERSTICS
GESR902P	700-750	12-28	75-85	High flow
GESR903P	750-800	30-45	85-98	High flow
GESR924	720-770	22-35	85-97	High flow