

Taffy Method type 300 Series

TRADE NAME	EPOXY EQUIVALENCY (g/eq)	SOLUTION VISCOSITY (G-H/25°C)	SOFTENING POINT(°C)	COLOR (Gardner)	CHARACTERSTICS
GESR307	1750-2100	Y-Z1	117-127	1MAX	For can coatings
GESR309	2400-3000	Z2-Z4	130-145	1MAX	For can coatings