

Cresol Novolac Type

TRADE NAME	EPOXY EQUIVALENCY (g/eq)	COLOR (Gardner)	SOFTENING POINT(°C)	CHARACTERSTICS
GECN701	190~215	3.0 MAX	60~64	Cresol novolac epoxy resin
GECN702	190-215	3.0 MAX	65-74	Cresol novolac epoxy resin
GECN703	195-225	3.0 MAX	75-85	Used in CFRP,CCL,coatings
GECN704	200-220	3.0 MAX	85-95	Higher molecular weight than GECN703